

**PERMANENT POOL WATERPROOFING
(EXISTING CONSTRUCTION) WITH
PENETRON® INTEGRAL CAPILLARY
WATERPROOFING OR WITH CEMENT BASE
POLYMER MODIFIED WATERPROOFING
COATING**



INTRODUCTION: Existing concrete swimming pools, are called those, that are fully constructed with landscaped garden or surrounding surfaces (covered with tile, wood, marble, etc.) or bordering with other concrete constructions, such as building, basements, garages, tunnels, etc. Also, there are incomplete pools with existing concrete walls, or, in some cases, with cementitious screed layer, but without a finished surface (tiles, paint, etc.).

I. Pool waterproofing in the existing concrete surface.

1. Repairing and waterproofing of honeycombed areas, tie holes and pointing applications, with the crystalline waterproofing system of the liquid applied, PENETRON® and the repairing PENECRETE MORTAR® and repair of cracks with running water with the crystalline waterproofing rapid set waterplug, PENEPLUG®.

Depending on the working procedures, concrete surface can be treated and cleaned by a high pressure jet water blasting (300-500 bar), for better visual contact with faulty areas.

Then, the water leaking cracks can be sealed with the rapid-setting crystalline waterproofing plug PENEPLUG® (mix with minimum water until the texture is as dry-earth). For a better application of PENEPLUG®, cracks should be routed out with mechanical means, up to 2 – 3 cm in width, in a conical shape, for better anchoring of the rapid-setting plug, during the application. Cold joints can be treated in a similar way, by cutting on both sides of the joint with mechanical means and creating a wedge, 3 cm in width. Next, rapid-setting plug PENEPLUG® is applied.



In some cases, depending on the work schedule, PENEPLUG® can be used as a waterplug, prior to water blasting, but only after PENEPLUG® has reached its mechanical strength. It must be pointed out, that 1 – 2 layers of the integral crystalline waterproofing coating PENETRON®, at a mixing ratio of 5 parts PENETRON® powder to 3-3.5 parts water (by volume), must be applied on PENEPLUG®, by brush, while the latter is still “tacky” and the total consumption of PENETRON® mixture is 1.5 kg/m² in total for 2 layers (depending on the surfaces, the indicative consumption should be between 1.1 to 1,6 kg / m²).

Cracks, honeycombed and spalled areas of new or existing concreting, should be routed out with mechanical means, to remove dirt, loose materials and aggregates. Tie holes must be repaired, as follows. Areas should be chiseled back to sound concrete, by mechanical means and an area of 1.4” (35 mm) around them and ¾” – 1.2” (20 -30 mm) in depth. Metal formworks must be saw cut in ¾” (20 mm) in depth. Wooden formworks must be removed completely or routed out at a reverse wedge of 1.2”x1.2”x1.6” (30 x 30 x 40 mm). Clean honeycombed or spalled areas and holes with excess water, to remove loose materials and moisten the surface to a dull dampness, which is prerequisite for the application of the liquid applied integral crystalline waterproofing coating, PENETRON®, and crystalline waterproofing mortar, PENECRETE MORTAR®. When the concrete is damp, with no wet sheen on the surface, apply a slurry coat of PENETRON®, at a mixing ratio of 5 part PENETRON® powder to 3-3.5 parts of water (by volume), on the areas to be patched or repaired and 2/5” (10 mm) around them. While PENETRON® coating is still “green” (tacky), mix PENECRETE MORTAR® with adequate amount of water, until the desired consistency is achieved [usual mixing ratio is 4.5 parts of PENECRETE MORTAR® to 1 part of water (by volume)] and fill the cracks and spalled areas. When



PENECRETE MORTAR® has been set, but is still moist, apply a second layer of PENETRON® slurry coat, on the repaired areas.

2. Application of Penetron® integral capillary waterproofing system.

It is possible to apply liquid integral crystalline waterproofing coating, PENETRON®, either in the internal or the external surface of the pool (required excavation of the surrounding area of the pool). Alternatively, the application of SEALCOAT™ FLEX (22.68 kg PENETRON® SEALCOAT with the mixing of 4 kg PENECRYL™ ELASTIC and 3 kg water, with fiberglass mesh reinforcement or not) is possible, in the external surface of the pool. Furthermore, the application of two components polyurethane/asphalt elastomeric resin PENECONAT™ HYPER ELASTIC BLACK is possible. After the application of PENETRON® SYSTEM, the wetting of PENETRON® for 1-2 days is necessary, in order to activate the crystal growth system. PENETRON® should be cured sufficiently. According to general directives for cement curing, PENETRON® SYSTEM should cure for 10-12 days, prior to water exposure.



3. Neutralization

As the application of PENETRON® products on the concrete surface causes the formation of silicic salts, not only in the concrete matrix, but most of the times on the surface of application as well (usually after the first 48 hours since application), there is a technical issue, regarding the reduced adhesion of decorative coatings or paints. The problem is treated with the "neutralization" procedure. Neutralization is actually the good "wash" of the surface, approx. after 3 weeks, since the application of PENETRON® products (adequate time for the PENETRON® to act), with a low acidity "aggression" hydrochloric acid (HCl) aqueous solution 3-8% in content or a vinegar solution in water (at a mixing ration 1:3 to 1:10, depending on the vinegar acidity).

During the application, after the surface is cleaned with a vacuum cleaner, use a brush and a plastic pail, containing the solution for the neutralization, "wash" the surface with the solution and after a few minutes, wash the surface with excess water. Then, the surface, after it is dry, can be coated or painted. Alternatively, decorative screeds can be applied within the first 48 hours and before the formation of the silicic acids on the surface. In that case, the time for the coating application is minimized, but the drawback is the inability to control the correct application and the system's operation. Also, there is always a small possibility for a percent of the formed crystals to penetrate the coatings or screeds and appear on the surface.



4. Application of a bonding layer and roughcasting / cementitious mortar to cover the concrete elements and smooth the walls and the bottom of the pool.

At first, a bonding layer is applied on the concrete elements, prior to the application of the cementitious screed for filling. As a bonding layer, either the acrylic resin PENETRON® ACRYLIC BONDCRETE™ or PRIMER STX 100™

can be applied, undiluted, with an indicative coverage of 199.7 ft²/gal (4.9 m²/Lt) or spatterdash, which consists of a mixture of 1 part of cement and 2-3 parts of sand (by volume), diluted in an aqueous solution of 1 part of acrylic resin PENETRON® LATEX and two parts of water (by volume).

Then, «drivers» are cast, prior to roughcasting/cementitious mortar application. «Drivers» and roughcasting consist of 1 part of cement and 3 parts of sand (by volume), diluted in an aqueous solution of 1 part of acrylic resin PENETRON® LATEX and two or three parts of water (by volume). The addition of polypropylene fibers is highly recommended, to avoid cracking. The cement percent of both mixtures is 400-500 kg/m³. PENETRON ADMIX® (0.8 – 1%) can be added as well.

NOTE: In all previous applications, avoid the use of limestone.

5. Finishing cementitious screed layer (fine or grater).

After the application of the cementitious mortar (roughcasting) on the walls and bottom surface of the pool for smoothing, a fine layer of cementitious screed, with fine-grade aggregates and thorough finishing follows, most of the times. This application is important, especially when a polyurethane coating for pools is applied (PENECOAT™ POOL).

This fine finishing cementitious screed layer consists of common materials, such as fine graded sand and quartz aggregates and high cement concentration (>400 kg/m³). Alternatively, PENETRON® TOP FINISH FINE, finishing topping cement mortar with polymers and fine graded quartz aggregates, can be applied, in an indicative consumption of 8.4 lb/ft² per inch thickness (1.6 kg/m² per mm thickness), usually in grey or white color. The use of the acrylic resin PENETRON® ACRYLIC BONDCRETE™, as a primer, is recommended.

6. Waterproofing of the concrete surface with the conventional systems SEALCOAT™ FLEX or SEALCOAT™ ELASTIC.

In most applications with ceramic tiles as a finish layer, the waterproofing of the surface, prior to tile application, is recommended. The two component liquid-applied waterproofing coating, SEALCOAT™ FLEX [flexible system of 50 lb (22.68 kg) PENETRON® SEALCOAT diluted in 8.8 lb (4 kg) PENECRYL™ ELASTIC and 6.6 lb (3 kg water)] or SEALCOAT™ ELASTIC [elastic system of 50 lb (22.68 kg) PENETRON® SEALCOAT diluted in 26.5 lb (12 kg) PENECRYL™ ELASTIC] can be used, regarding the demands of the application, which is crack bridging of capillary cracks. Apply uniformly a slurry coat of SEALCOAT™ FLEX or SEALCOAT™ ELASTIC, with a nap roller. The next day, apply a vertical second layer. The coverage is approx. 0,4 lb/ft² (2 kg/m²) in two layers, for SEALCOAT™ FLEX and approx. 0.5 lb/ft² (2.5kg/m²) in two layers, for SEALCOAT™ ELASTIC. Furthermore, the SEALCOAT™ SYSTEMS can be reinforced with a fiberglass grid between layers (mesh 5x5 mm). In that type of application, place the grid on the first layer, while wet, and fully cover the grid with the second layer, on the next day. If necessary, apply a third layer of SEALCOAT™ FLEX or SEALCOAT™ ELASTIC. The use of fiberglass grid is expected to increase the total coverage of the system up to approx. 0.6 lb/ft² (3 kg/m²) in three layers.

If the cementitious screed layer has no cracks, the application of SEALCOAT™ FLEX is possible. In case there are many cracks in the surface, SEALCOAT™ ELASTIC should be applied.

In order to place ceramic tiles on top of SEALCOAT™ SYSTEMS, use an appropriate FLEX type adhesive paste, for pool application.

7. Application of PENEBAR® SW in pipes and pool accessories.

In case of pipes application, the sealing/waterproofing of the pipes' perimeter with PENEBAR® SW is necessary (usually PENEBAR® SW 55 TYPE B or half of PENEBAR® SW 55 TYPE B is suggested). The PENEBAR® SW should be put in 5 cm depth and covered with rapid setting integral crystalline cementitious waterstop, PENEPLUG®.



II. Waterproofing and repairing of existing pool failures with tiles or chipping in the topping surface.

A. In case there are failures in the topping surface of the existing pool, with tiles or chippings, cracks and water loss, the tiles or chippings should be removed and the cracks should be repaired with repairing mortar.

1A. Dismantling of tiles or chippings and checking of cementitious screed layer.

First of all, the dismantling of tiles or chippings, or the removal of colors and the check of cementitious screed layer for failures is required. If the cementitious screed layer is healthy, the surfaces to be treated must be clean and sound, free of dirt and any other contaminant, that will act as a bond breaker of repairing mortars. Surface must be saturated with water, without any standing or puddled water. If needed, apply a bonding agent, PENETRON® ACRYLIC BONDCRETE, to enhance bonding properties, before PENETRON® MULTI PATCH or PENETRON® ACRYLIC PATCH application. PENETRON® MULTI PATCH requires 3,1 to 3,4 kg of clean water per bag, while PENETRON® ACRYLIC PATCH requires 4,7 to 5 kg clean water per bag. For thickness over 5 cm, add 25% by weight of PENETRON® ACRYLIC PATCH, QUARTZ SAND MIX diameter up to 1 cm. For quick repair of concrete with hydrostatic pressure, apply the highly accelerated underwater cement, PENETRON® WATERPLUG RAPID. Apply immediately after mixing. As soon as PENETRON® WATERPLUG RAPID has achieved a dry, putty texture and a compatible shape, or a dry pack (dry earth) consistency, depending on the application, force the material into the crack or cavity, compressing it firmly, using a gloved palm, trowel, wood block, or other flat object. Hold it in place for over a minute. If there is a strong water flow, hold for six minutes. Do not brush or trowel over surface. Shave off excess material with a knife or other similar sharp tool.

2A. Waterproofing of the concrete surface with the conventional systems SEALCOAT™ FLEX or SEALCOAT™ ELASTIC.

In most applications with ceramic tiles as a finishing layer, the waterproofing of the surface, prior to tile application, is recommended. The two component, liquid-applied, waterproofing coating, SEALCOAT™ FLEX [flexible system of 50 lb (22.68 kg) PENETRON® SEALCOAT diluted in 8.8 lb (4 kg) PENECRYL™ ELASTIC and 6.6 lb (3 kg water)], or SEALCOAT™ ELASTIC [elastic system of 50 lb (22.68 kg) PENETRON® SEALCOAT diluted in 26.5 lb (12 kg) PENECRYL™ ELASTIC] can be used, regarding the demands of the application, which is crack bridging of capillary cracks. Apply uniformly a slurry coat of SEALCOAT™ FLEX or SEALCOAT™ ELASTIC, with a nap roller. The next day, apply a vertical second layer. The coverage is approx. 0,4 lb/ft² (2 kg/m²) in two layers, for SEALCOAT™ FLEX and approx. 0.5 lb/ft² (2.5kg/m²) in two layers, for SEALCOAT™

ELASTIC. Furthermore, the SEALCOAT™ SYSTEMS can be reinforced with a fiberglass grid between layers (mesh 5x5 mm). In that type of application, place the grid on the first layer, while wet, and fully cover the grid with the second layer, on the next day. If necessary, apply a third layer of SEALCOAT™ FLEX or SEALCOAT™ ELASTIC. The use of fiberglass grid is expected to increase the total coverage of the system up to approx. 0.6 lb/ft² (3 kg/m²) in three layers.

If the cementitious screed layer has no cracks, the application of SEALCOAT™ FLEX is possible. In case there are many cracks in the surface, SEALCOAT™ ELASTIC should be applied.

In order to place ceramic tiles on top of SEALCOAT™ SYSTEMS, use an appropriate FLEX type adhesive paste for pool application.



B. In case there are failures in the topping surface of the existing pool, with tiles or chippings and there are cracks and water loss, the tiles or chippings should be removed, the cracks should be repaired with repairing mortar and the concrete should be repaired with crystalline waterproofing coating.

First of all, the dismantling of tiles or chippings is required or the removal of colors and the checking of cementitious screed layer for failures. If the cementitious screed layer is not healthy, then the dismantling of cementitious screed layer is required, by a high pressure jet waterblasting (300-500 bar).

Depending on the working procedures, concrete surface can be treated and cleaned by a high pressure jet waterblasting (300-500 bar), for better visual contact with faulty areas.

Then, the water leaking cracks can be sealed with the rapid-setting crystalline waterproofing plug, PENEPLUG® (mix with minimum water, until the texture is as dry-earth). For a better application of PENEPLUG®, cracks should be routed out with mechanical means, up to 2 – 3 cm in width, in a conical shape, for better anchoring of the rapid-setting plug, during the application. Cold joints can be treated in a similar way, by cutting on both sides of the joint with mechanical means and creating a wedge, 3 cm in width. Next, rapid-setting plug, PENEPLUG®, is applied.

In some cases, depending on the work schedule, PENEPLUG® can be used as a waterplug, prior to waterblasting, but only after PENEPLUG® has reached its mechanical strength. It must be pointed out, that 1 – 2 layers of the integral crystalline waterproofing coating, PENETRON®, at a mixing ratio of 5 parts PENETRON® powder to 3-3.5 parts water (by volume), must be applied on PENEPLUG®, by brush, while the latter is still “tacky” and the total consumption of PENETRON® mixture is 1.5 kg/m² in total for 2 layers (depending on the surfaces, the indicative consumption should be between 1.1 to 1,6 kg / m²).

Tie holes must be repaired, as mentioned below. Areas should be chiseled back to sound concrete, by mechanical means and the area of 1.4” (35 mm) around them and metal formworks must be removed or, at least, sawcut and routed out at a reverse wedge of 1.2”x1.2”x1.6” (30 x 30 x 40 mm). Clean areas with excess water, to remove loose materials and moisten the surface to a dull dampness, as mentioned above. When the concrete is damp, with no wet sheen on the surface, apply a slurry coat of the integral crystalline waterproofing coating PENETRON®, on the areas to be patched or repaired and 2/5” (10 mm) around them, at a mixing ratio of 5 part PENETRON® powder to 3-3.5 parts of water (by volume).

While PENETRON® coating is still “green” (tacky), mix the integral crystalline repairing mortar PENECRETE MORTAR® with adequate amount of water, until the desired consistency is achieved [usual mixing ratio is 4.5 parts of PENECRETE MORTAR® to 1 part of water (by volume)] and fill the cracks and spalled areas. As mentioned above, when PENECRETE MORTAR® has set, but is still moist, apply a second layer of

PENETRON® slurry coat, at a mixing ratio of 5 part PENETRON® powder to 3-3.5 parts of water (by volume), on the repaired areas. At this stage, if waterproofing of the total construction is required, apply a slurry coat of PENETRON® on the whole surface, in two layers, while the first layer is still “green” (approx. half to one hour later).

In lots of applications, to save time, the first layer of PENETRON® is applied post to surface preparation and dampening and approx. half an hour later, while the product is still “green” and the repairing mortar, PENECEMTE MORTAR®, is applied. Approx. half to an hour later, and while PENECEMTE MORTAR® is still “green”, the second layer of PENETRON® slurry coat is applied. The total consumption of the two layers of PENETRON® is 1.5 kg/m^2 (depending on the surfaces, the indicative consumption should be between 1.1 to $1,6 \text{ kg / m}^2$).

2B. Application of Penetron® integral capillary waterproofing system.

It is possible to apply liquid integral crystalline waterproofing coating, PENETRON®, either in the internal or the external surface of the pool (required excavation of the surrounding area of the pool). Alternatively, in the external surface of the pool, the application of SEALCOAT™ FLEX (22.68 kg PENETRON® SEALCOAT with the mixing of 4 kg PENECEMTE ELASTIC and 3 kg water, with fiberglass mesh reinforcement or not) is possible. Furthermore, the application of two components polyurethane/asphalt elastomeric resin, PENECEMTE HYPER ELASTIC BLACK is possible. After the application of PENETRON® SYSTEM, the wetting of PENETRON® for 1-2 days is necessary, in order to activate the crystal growth system. PENETRON® should be cured sufficiently. Accordingly to general directives for cement curing, PENETRON® SYSTEM should cure for 10-12 days, prior to water exposure.



3B. Neutralization

As the application of PENETRON® products on the concrete surface cause the formation of silicic salts, not only in the concrete matrix, but most of the times on the surface of application as well (usually after the first 48 hours since application), there is a technical issue, regarding the reduced adhesion of decorative coatings or paints. The problem is treated with the “neutralization” procedure. Neutralization is actually the good “wash” of the surface, approx. after 3 weeks, since the application of PENETRON® products (adequate time for the PENETRON® to act), with a low acidity “aggression” hydrochloric acid (HCl) aqueous solution 3-8% in content or a vinegar solution in water (at a mixing ration 1:3 to 1:10, depending on the vinegar acidity).

During the application, after the surface is cleaned with a vacuum cleaner, use a brush and a plastic pail, containing the solution for the neutralization, “wash” the surface with the solution and after a few minutes, wash the surface with excess water. Then, the surface, after it is dry, can be coated or painted. Alternatively, for the use of decorative screeds, they can be applied within the first 48 hours and before the formation of the silicic acids on the surface. In that case, the time for the coating application is minimized, but the drawback is the inability to control the correct application and operation of the system. Also, in that case, there is always a small possibility for a percent of the formed crystals to penetrate the coatings or screeds and appear on the surface.

4B. Application of a bonding layer and roughcasting / cementitious mortar to cover the concrete elements and smooth the walls and the bottom of the pool.

At first, a bonding layer is applied on the concrete elements, prior to the application of the cementitious screed, for filling. As a bonding layer, either the acrylic resin PENETRON® ACRYLIC BONDCRETE™ or PRIMER STX 100™ can be applied, undiluted, with an indicative coverage of 199.7 ft²/gal (4.9 m²/Lt) or spatterdash, which consists of a mixture of 1 part of cement and 2-3 parts of sand (by volume), diluted in an aqueous solution of 1 part of acrylic resin, PENETRON® LATEX and two parts of water (by volume).

Then, «drivers» are cast, prior to roughcasting/cementitious mortar application. «Drivers» and roughcasting consist of 1 part of cement and 3 parts of sand (by volume), diluted in an aqueous solution of 1 part of acrylic resin, PENETRON® LATEX and two or three parts of water (by volume). The addition of polypropylene fibers is highly recommended, to avoid cracking. The cement percent of both the mixtures is 400-500 kg/m³. PENETRON ADMIX® (0.8 – 1%) can be added as well.

NOTE: In all previous applications, avoid the use of limestone.

5B. Finishing cementitious screed layer (fine or grater).

After the application of the cementitious mortar (roughcasting) on the walls and bottom surface of the pool for smoothing, follows, most of the times, a fine layer of cementitious screed, with fine-grade aggregates and thorough finishing. This application is important, especially when a polyurethane coating for pools is applied (PENECOAT™ POOL).

This fine finishing cementitious screed layer consists of common materials, such as fine graded sand and quartz aggregates and high cement concentration (>400 kg/m³). Alternatively, PENETRON® TOP FINISH FINE, finishing topping cement mortar with polymers and fine graded quartz aggregates can be applied, in an indicative consumption of 8.4 lb/ft² per inch thickness (1.6 kg/m² per mm thickness), usually in grey or white color. The use of the acrylic resin, PENETRON® ACRYLIC BONDCRETE™, as a primer, is recommended.



Application of PENEBAR® SW in pipes and pool accessories.

In case of pipes application, the sealing/waterproofing of the pipes' perimeter with PENEBAR® SW is necessary (usually PENEBAR® SW 55 TYPE B or half of PENEBAR® SW 55 TYPE B is suggested). The PENEBAR® SW should be put in 5 cm depth and covered with rapid setting integral crystalline cementitious waterstop, PENEPLUG®.

III. Waterproofing and repairing of existing pool failures, with color in the topping surface.

A. In case there are failures in the topping surface of the existing pool with tiles or chippings and there are cracks and water loss, the tiles or chippings should be removed and the cracks should be repaired, with repairing mortar.

1A. Color removal and checking of cementitious screed layer.

First of all, remove colors and check cementitious screed layer for failures. If the cementitious screed layer is healthy, then the surfaces to be treated must be clean and sound, free of dirt and any other contaminant that will act as a bond breaker of repairing mortars. Surface must be saturated with water, without any standing or puddled water. If needed, apply a bonding agent, PENETRON® ACRYLIC BONDCRETE, to enhance bonding properties, before PENETRON® MULTI PATCH or PENETRON® ACRYLIC PATCH application. PENETRON® MULTI PATCH requires 3,1 to 3,4 kg of clean water per bag, while PENETRON® ACRYLIC PATCH requires 4,7 to 5 kg clean water per bag. For thickness over 5 cm, add 25% by weight of PENETRON® ACRYLIC PATCH, QUARTZ SAND MIX diameter up to 1 cm. For quick repair work of concrete with hydrostatic pressure, apply the

highly accelerated underwater cement, PENETRON® WATERPLUG RAPID. Apply immediately after mixing. As soon as PENETRON® WATERPLUG RAPID has achieved a dry, putty texture and a compatible shape, or a dry pack (dry earth) consistency, depending on the application, force the material into the crack or cavity, by compressing it firmly, using a gloved palm, trowel, wood block or other flat object. Hold it in place for over a minute. If there is a strong water flow, hold for six minutes. Do not brush or trowel over surface. Shave off excess material with a knife or other similar sharp tool.

2A. Waterproofing of the concrete surface with the conventional systems SEALCOAT™ FLEX or SEALCOAT™ ELASTIC.

In most applications with ceramic tiles as a finishing layer, the waterproofing of the surface, prior to tile application, is recommended. The two component liquid-applied waterproofing coating, SEALCOAT™ FLEX [flexible system of 50 lb (22.68 kg), PENETRON® SEALCOAT, diluted in 8.8 lb (4 kg), PENECRYL™ ELASTIC and 6.6 lb (3 kg water)] or SEALCOAT™ ELASTIC [elastic system of 50 lb (22.68 kg), PENETRON® SEALCOAT, diluted in 26.5 lb (12 kg), PENECRYL™ ELASTIC] can be used, regarding the demands of the application, which is crack bridging of capillary cracks. Apply uniformly a slurry coat of SEALCOAT™ FLEX or SEALCOAT™ ELASTIC, with a nap roller. The next day, apply a vertical second layer. The coverage is approx. 0.4 lb/ft² (2 kg/m²) in two layers, for SEALCOAT™ FLEX and approx. 0.5 lb/ft² (2.5kg/m²) in two layers, for SEALCOAT™ ELASTIC. Furthermore, the SEALCOAT™ SYSTEMS can be reinforced with a fiberglass grid between layers (mesh 5x5 mm). In that type of application, place the grid on the first layer, while wet, and fully cover the grid with the second layer, on the next day. If necessary, apply a third layer of SEALCOAT™ FLEX or SEALCOAT™ ELASTIC. The use of fiberglass grid is expected, to increase the total coverage of the system, up to approx. 0.6 lb/ft² (3 kg/m²) in three layers.



If the cementitious screed layer has not cracks, the application of SEALCOAT™ FLEX is possible. In case there are many cracks in the surface, SEALCOAT™ ELASTIC should be applied.

In order to place ceramic tiles on top of SEALCOAT™ SYSTEMS, use an appropriate FLEX type adhesive paste for pool application.

B. In case there are failures in the topping surface of the existing pool, with tiles or chippings and there are cracks and water loss, the tiles or chippings should be removed, the cracks should be repaired with repairing mortar and the concrete should be repaired with crystalline waterproofing coating.

First of all, remove colors and check of cementitious screed layer for failures. If the cementitious screed layer is not healthy, then the dismantling of cementitious screed layer is required, by a high pressure jet waterblasting (300-500 bar).

Depending on the working procedures, concrete surface can be treated and cleaned by a high pressure jet waterblasting (300-500 bar), for better visual contact with faulty areas.

Then, the water leaking cracks can be sealed with the rapid-setting crystalline waterproofing plug, PENEPLUG® (mix with minimum water, until the texture is as dry-earth). For a better application of PENEPLUG®, cracks should be routed out with mechanical means, up to 2 – 3 cm in width, in a conical shape, for better anchoring of the rapid-setting plug, during the application. Cold joints can be treated in a similar way, by cutting on both sides of the joint, with mechanical means and creating a wedge, 3 cm in width. At next, rapid-setting plug, PENEPLUG® is applied.

In some cases, depending on the work schedule, PENEPLUG® can be used as a waterplug, prior to waterblasting, but only after PENEPLUG® has reached its mechanical strength. It must be pointed out, that 1 – 2 layers of the integral crystalline waterproofing coating PENETRON®, at a mixing ratio of 5 parts PENETRON® powder to 3-3.5 parts water (by volume), must be applied on PENEPLUG®, by brush, while the latter is still “tacky” and the total consumption of PENETRON® mixture is 1.5 kg/m² in total for 2 layers (depending on the surfaces, the indicative consumption should be between 1.1 to 1,6 kg / m²).

Tie holes must be repaired, as mentioned below. Areas should be chiseled back to sound concrete, by mechanical means and the area of 1.4” (35 mm) around them and metal formworks must be removed, or, at least, sawcut and routed out at a reverse wedge of 1.2”x1.2”x1.6” (30 x 30 x 40 mm). Clean areas with excess water, to remove loose materials and moisten the surface to a dull dampness, as mentioned above. When the concrete is damp, with no wet sheen on the surface, apply a slurry coat of the integral crystalline waterproofing coating PENETRON®, on the areas to be patched or repaired and 2/5” (10 mm) around them, at a mixing ratio of 5 part PENETRON® powder to 3-3.5 parts of water (by volume).

While PENETRON® coating is still “green” (tacky), mix the integral crystalline repairing mortar PENECRETE MORTAR® with adequate amount of water, until the desired consistency is achieved [usual mixing ratio is 4.5 parts of PENECRETE MORTAR® to 1 part of water (by volume)] and fill the cracks and spalled areas. As mentioned above, when PENECRETE MORTAR® has set, but is still moistened, apply a second layer of PENETRON® slurry coat, at a mixing ratio of 5 part PENETRON® powder to 3-3.5 parts of water (by volume), on the repaired areas. At this stage, if waterproofing of the total construction is required, apply a slurry coat of PENETRON® on the whole surface, in two layers, while the first layer is still “green” (approx. half to one hour later).

In lots of applications, to save time, the first layer of PENETRON® is applied post to surface preparation and dampening and approx. half an hour later, while the product is still “green”, the repairing mortar PENECRETE MORTAR® is applied. Approx. half to an hour later, and while PENECRETE MORTAR® is still “green”, the second layer of PENETRON® slurry coat is applied. The total consumption of the two layers of PENETRON® is 1.5 kg/m² (depending on the surfaces, the indicative consumption should be between 1.1 to 1,6 kg / m²).

2B. Application of Penetron® integral capillary waterproofing system.

It is possible to apply liquid integral crystalline waterproofing coating, PENETRON®, either in the internal or the external surface of the pool (required excavation of the surrounding area of the pool). Alternatively, the application of SEALCOAT™ FLEX (22.68 kg PENETRON® SEALCOAT with the mixing of 4 kg PENECRYL™ ELASTIC and 3 kg water, with fiberglass mesh reinforcement or not) is possible, in the external surface of the pool. Furthermore, the application of two components polyurethane/asphalt elastomeric resin, PENECONAT™ HYPER ELASTIC BLACK, is possible. After the application of PENETRON® SYSTEM, the wetting of PENETRON® is necessary for 1-2 days, in order to activate the crystal growth system. PENETRON® should be cured sufficiently. According to general directives for cement curing, PENETRON® SYSTEM should cure for 10-12 days, prior to water exposure.

3B. Neutralization

As the application of PENETRON® products on the concrete surface cause the formation of silicic salts, not only in the concrete matrix, but most of the times on the surface of application as well (usually after the first 48 hours since application), there is a technical issue, regarding the reduced adhesion of decorative coatings or paints. The problem is treated with the “neutralization” procedure. Neutralization is actually the good “wash” of the surface, approx. after 3 weeks, since the application of PENETRON® products (adequate time for the PENETRON® to act), with a low acidity “aggression” hydrochloric acid (HCl) aqueous solution 3-8% in content, or a vinegar solution in water (at a mixing ration 1:3 to 1:10, depending on the vinegar acidity).

During the application, after the surface is cleaned with a vacuum cleaner, use a brush and a plastic pail, containing the solution for the neutralization, “wash” the surface with the solution and after a few minutes, wash the

surface with excess water. Then, the surface, can be coated or painted, after it is dry. Alternatively, for the use of decorative screeds, they can be applied within the first 48 hours and before the formation of the silicic acids on the surface. In that case, the time for the coating application is minimized, but the drawback is the inability to control the correct application and operation of the system. Also, in that case, there is always a small possibility for a percent of the formed crystals to penetrate the coatings or screeds and appear on the surface.

4B. Application of a bonding layer and roughcasting / cementitious mortar to cover the concrete elements and smooth the walls and the bottom of the pool.

At first, a bonding layer is applied on the concrete elements, prior to the application of the cementitious screed for filling. As a bonding layer, either the acrylic resin, PENETRON® ACRYLIC BONDCRETE™ or PRIMER STX 100™ can be applied, undiluted, with an indicative coverage of 199.7 ft²/gal (4.9 m²/Lt) or spatterdash, which consists of a mixture of 1 part of cement and 2-3 parts of sand (by volume), diluted in an aqueous solution of 1 part of acrylic resin, PENETRON® LATEX and two parts of water (by volume).

Then, «drivers» are cast, prior to roughcasting/cementitious mortar application. «Drivers» and roughcasting consist of 1 part of cement and 3 parts of sand (by volume), diluted in an aqueous solution of 1 part of acrylic resin, PENETRON® LATEX and two or three parts of water (by volume). The addition of polypropylene fibers is highly recommended, to avoid cracking. The cement percent of both the mixtures is 400-500 kg/m³. PENETRON ADMIX® (0.8 – 1%) can be added as well.

NOTE: In all previous applications, avoid the use of limestone.

5B. Finishing cementitious screed layer (fine or grater).

After the application of the cementitious mortar (roughcasting) on the walls and bottom surface of the pool for smoothing, follows, most of the times, a fine layer of cementitious screed, with fine-grade aggregates and thorough finishing. This application is important, especially when a polyurethane coating for pools is applied (PENECOAT™ POOL).




This fine finishing cementitious screed layer consists of common materials, such as fine graded sand and quartz aggregates and high cement concentration (>400 kg/m³). Alternatively, PENETRON® TOP FINISH FINE, finishing topping cement mortar with polymers and fine graded quartz aggregates, can be applied, in an indicative consumption 8.4 lb/ft² per inch thickness (1.6 kg/m² per mm thickness), usually in grey or white color. The use of the acrylic resin, PENETRON® ACRYLIC BONDCRETE™, as a primer, is recommended.


C. In case of existing pool with failure in the pool paint, the polyurethane paint, PENECOAT™ POOL, must be applied.

In case of PENECOAT™ POOL application on old pool coating (eg. epoxy coatings), or surfaces, with low mechanical strength, grinding of the surface is required, prior to application, with a grinding machine, to remove considerable thickness, to remove polishing and roughen the surface. Cracks can be repaired with PENETRON® MULTIPATCH or PENETRON® ACRYLIC PATCH. If needed, apply a bonding agent, PENETRON® ACRYLIC BONDCRETE, to enhance bonding properties, before PENETRON® MULTI PATCH or PENETRON® ACRYLIC PATCH application. PENETRON® MULTI PATCH requires 3,1 to 3,4 kg of clean water per bag, while PENETRON® ACRYLIC PATCH requires 4,7 to 5 kg clean water per bag. For thickness over 5 cm add 25% by weight of PENETRON® ACRYLIC PATCH, QUARTZ SAND MIX diameter up to 1 cm.

To enhance adhesion and stabilization, we recommend adding the water-based epoxy primer, PENEPOX™ W. Dilution of PENEPOX™ W with water, at a ratio of 10 to 20% (by weight), is highly recommended, at an indicative consumption between 180-200 gr/m². The application of the polyurethane-based paint PENECOAT™ POOL is made within 12 to 24 hours (lower temperatures period), while, at normal temperatures, is recommended within 2-3 hours.

Note: Maximum moisture content should not exceed 5%.





The description texts mentioned above are not subject of a case study, but technical propositions, according to our best of knowledge and based on our experience and knowledge up to date. For more information, regarding the safe use, treatment and storage of our products, contact PENETRON HELLAS and refer to the *Product Data Sheet* and *Material Safety Data Sheet* of every product you use.